

(12) UK Patent Application (19) GB (11) 2 306 486 (13) A

(43) Date of A Publication 07.05.1997

(21) Application No 9622074.4

(22) Date of Filing 23.10.1996

(30) Priority Data

(31) 19539315 (32) 23.10.1995 (33) DE

(71) Applicant(s)

Hoechst Aktiengesellschaft

(Incorporated in the Federal Republic of Germany)

D-65926 Frankfurt am Main,
Federal Republic of Germany

(72) Inventor(s)

Andreas Schrell
Stefan Meier

(74) Agent and/or Address for Service

Abel & Imray
Northumberland House, 303-306 High Holborn,
LONDON, WC1V 7LH, United Kingdom

(51) INT CL⁶

C08L 1/00 1/24 , C09K 11/08 , D01F 2/06

(52) UK CL (Edition O)

C3K KDA K121 K123 K124 K125 K126 K127 K128 K129
C3V VEE
C3W W121
U1S S1570

(56) Documents Cited

US 4665788 A

(58) Field of Search

UK CL (Edition O) C3K KDA , C3V VEE
INT CL⁶ C08L 1/00 1/02 1/22 1/24 , C09K 11/08 11/57
11/58 11/59 11/60 11/61 11/70 11/71 11/77 11/78
11/79 11/81 , D01F 2/00 2/06 2/08 2/10
ONLINE:WPI

(54) Luminescent regenerated cellulose fibre

(57) Luminescent regenerated cellulose fibre comprising one or more inorganic luminophors selected from the group consisting of the phosphates, tungstates, oxides, silicates and aluminates of the alkaline earth metals, of the transition elements or of the rare earths and the halides of the alkali and alkaline earth metals doped with one or more activators selected from the group consisting of Mn^{2+} , Mn^{4+} , Sb^{3+} , Sn^{2+} , Pb^{2+} , Cu^{+} , Ag^{+} and the ions of the rare earths, and also, a process for producing luminescent regenerated cellulose fibre that comprises adding an activator-doped inorganic luminophor to either a viscose dope or a cellulose solution and spinning fibre from the dope or solution.

GB 2 306 486 A

Luminescent regenerated cellulose fiber

The invention relates to the field of luminescent cellulose fibers.

10 Regenerated cellulose is generally colored by dyeing with water-soluble
dyes or vat dyes by the methods customary in textile dyeing for staples,
yarns, wovens and knits. Coloring as part of the spinning process, by
contrast, has hitherto only been possible with pigments, since these
coloring species are insoluble in water or organic solvents and thus remain
encapsulated in the viscose fiber during the subsequent washing
15 processes (Chemiefaser-Textilindustrie, vol. 34/86 (1984) No. 6, 444).

To brighten regenerated cellulose fiber, substantive brighteners which
absorb radiation within a broad UV range at about 250 - 360 nm and
fluoresce in the visible region at about 420 - 440 nm are added to the wash
20 baths downstream of the spinning process. If water-soluble brighteners are
used, the finished fiber will show poor washfastness properties, so that the
desired effect is only of limited duration. In addition, the lightfastness level
has to be classed as inadequate. A further disadvantage of these organic
UV-active compounds is their cost.

25 When UV-active pigments are encapsulated in the fiber, the result is
frequently a fiber having the self-color of the active substances or else a
fiber which appears very white to bluish white to the human eye.

30 Japanese Patent Publication 87-327866 describes the addition of yttrium
oxysulfide, but this pigment has the disadvantage that it loses its
luminescence during the grinding to particle sizes less than 1 μm , since
the luminescence effect depends on the crystal structure of the compound.
In addition, the sulfur moiety in the molecule is not sufficiently resistant to
35 the acidic spinning process, the subsequent desulfurization processes and

the oxidative processing steps which a viscous fiber routinely undergoes.

It is an object of the present invention to provide a
5 process for producing a substantially colorless regenerated cellulose fiber without the disadvantages described above. It is also desired to have a fiber material which will fluoresce only within a very narrow spectral range, preferably of about 10 to 20 nm. This object is
10 surprisingly achieved by mixing certain inorganic luminophors into the viscose dope and then spinning it into an acidic spin bath.

The present invention accordingly provides luminescent
15 regenerated cellulose fiber comprising one or more inorganic luminophors selected from the group consisting of the phosphates, oxides, tungstates, silicates and aluminates of the alkaline earth metals, of the transition elements or of the rare earths and the halides of the alkali and alkaline
20 earth metals doped with one or more activators selected from the group consisting of Mn^{2+} , Mn^{4+} , Sb^{3+} , Sn^{2+} , Pb^{2+} , Cu^{+} , Ag^{+} and the ions of the rare earths.

The term "inorganic luminophors" is to be understood
25 as meaning synthetic inorganic crystalline compounds capable of luminescing in the ultraviolet, X-ray or visible spectrum following energy absorption. In this process, known as

photoluminescence, the wavelength of the emission maximum is greater than that of the absorbed radiation.

5 The term "alkaline earth metals" is to be understood as meaning the elements of the second main group of the Periodic Table of the elements (i.e., Be, Mg, Ca, Sr, Ba, Ra).

10 The term "transition elements" is to be understood as meaning the elements 21 to 48 and 72 to 80 of the Periodic Table of the elements.

The term "rare earths" is to be understood as meaning the elements 57 to 71 of the Periodic Table of the elements.

15 In general, the ability to luminesce is acquired only by activation, i.e. through incorporation (doping) of small amounts of foreign ions (activators) in the crystal lattice of the inorganic compound (base material).

20 Particularly preferred inorganic luminophors are calcium phosphates, zinc silicates, strontium phosphates, alkaline earth metal silicates, silicates and aluminates of the rare earths, tungstates of the alkaline earth metals, zinc oxides and oxides of the rare earths.

25 Particularly preferred activators are Eu^{2+} , Eu^{3+} , Sb^{3+} , Mn^{2+} , Ag^{+} , Cu^{+} ,

Sn^{2+} and Tb^{3+} .

Of particular interest are the following luminophor-activator combinations:
zinc salts with Mn^{2+} , Cu^{+} or Ag^{+} as activators; barium magnesium
5 aluminate, $\text{Ba}(\text{Al},\text{Mg})_{11}\text{O}_{19}:\text{Eu}^{2+}$; strontium aluminate, $\text{SrAl}_2\text{O}_4:\text{Eu}^{2+}$;
yttrium oxide, $\text{Y}_2\text{O}_3:\text{Eu}^{3+}$; calcium halophosphate, $\text{Ca}_5(\text{PO}_4)_3(\text{F},\text{Cl}):\text{Sb}^{3+}$,
 Mn^{2+} ; strontium magnesium orthophosphate, $(\text{Sr},\text{Mg})_3(\text{PO}_4)_2:\text{Sn}^{2+}$; zinc
silicate $\text{Zn}_2\text{SiO}_4:\text{Mn}^{2+}$; cerium magnesium aluminate,
10 $\text{Ce}(\text{Mg},\text{Al})_{12}\text{O}_{19}:\text{Tb}^{3+}$.

It has been found that the activated base materials can be excited even
after encapsulation in a cellulose matrix and act luminescingly on
irradiation. This is especially surprising because most inorganic
luminophors are acid-labile and it was not foreseeable that these
15 compounds would survive the strongly acidic spinning process intact. The
luminophors emit light in narrow wavelength ranges of the visible
spectrum, of the near ultraviolet and of the infrared.

The preparation of luminophors and their doping with activators is well
20 known and has been repeatedly described in the literature, for example in
Ullmann, Lexikon der technischen Chemie, 4th edition, vol. 16, pages 180
ff. (1978).

Luminescent regenerated cellulose fiber of this invention includes the
25 inorganic luminophor in an amount of advantageously 0.01 to 5 % by
weight, preferably 0.2 to 3 % by weight, based on the cellulose content of
the spinning dope prior to coagulation and shaping.

The inorganic luminophors advantageously have an average particle size
30 of less than 1 μm , in particular 0.5 to 0.7 μm .

The present invention also provides a process for producing luminescent
regenerated cellulose fiber, which comprises adding the activator-doped
inorganic luminophor to the viscose dope and spinning fiber by the viscose

spinning process, or adding the luminophor to a cellulose solution and spinning fiber from the solution, for example by the cupro process, the lyocell process or the process involving low degree of substitution cellulose ethers.

5

More particularly, the cellulose is dissolved in a suitable organic solvent, for example N-methylmorpholine oxide/water, the luminophor is added to the solution in dispersed form, and the dope is directly spun into fiber.

10 The luminophors of this invention are highly compatible with the viscose. They are added in an amount of 0.01 to 5 % by weight, preferably 0.2 to 3 % by weight, based on the cellulose content of the spinning dope, prior to coagulation and shaping.

15 The examples which follow illustrate the invention. Parts are by weight.

Example 1

20 A commercial fiber-grade viscose having a cellulose content of 8.9 %, an alkali content of 5 % and a viscosity of 38 falling-ball seconds at 30°C is admixed with an inorganic luminophor as follows:
4.48 parts of yttrium oxide doped with europium, particle size less than 1 μm , are dispersed in 10 parts of water and mixed with 436 parts of fiber-grade viscose. This premix is stirred into 2522 parts of fiber-grade viscose.
25 After devolatilization, the spinning dope is spun by commercial viscose spinning processes into a sulfuric acid bath comprising sodium sulfate and zinc sulfate to form fiber, which is stretched in acidic baths, cut, washed, spin finished and dried. The fiber obtained, which has no self-color, has a red luminescence color on irradiation with light of wavelength 254 nm.

30

Example 2

Example 1 is repeated to mix 3 %, based on the cellulose mass in the viscose, of barium magnesium aluminate doped with europium into the

spinning dope.

Further processing by the operations customary for fiber-grade viscoses gives a modified-viscose fiber which on irradiation with light of wavelength 254 nm shows a blue luminescence color without itself being colored.

5

Example 3

Example 1 is repeated to mix 1 % of cerium magnesium aluminate comprising terbium as activator into the spinning dope. Processing by the further customary operations affords a fiber which on irradiation with light of wavelength 254 nm luminesces with a green luminescence color.

10

Examples 4 to 6

Example 1 is repeated each time to mix in each time 2 % of the below-mentioned luminophor:activator.

15

		Luminescence color:
20	4. calcium halophosphate : Sb^{3+}	light blue
	5. strontium magnesium orthophosphate : Sn^{2+}	reddish orange
	6. zinc silicate : Mn^{2+}	green.

CLAIMS :

1. Luminescent regenerated cellulose fiber comprising one or more inorganic luminophors selected from the group consisting of the phosphates, tungstates, oxides, silicates and aluminates of the alkaline earth metals, of the transition elements or of the rare earths and the halides of the alkali and alkaline earth metals doped with one or more activators selected from the group consisting of Mn^{2+} , Mn^{4+} , Sb^{3+} , Sn^{2+} , Pb^{2+} , Cu^{+} , Ag^{+} and the ions of the rare earths.
2. The luminescent regenerated cellulose fiber of claim 1, wherein the inorganic luminophors are selected from the group consisting of calcium phosphates, zinc silicates, strontium phosphates, alkaline earth metal silicates, silicates and aluminates of the rare earths, tungstates of the alkaline earth metals, zinc oxides and oxides of the rare earths.
3. The luminescent regenerated cellulose fiber of claim 1 or 2, wherein the activators are selected from the group consisting of Eu^{2+} , Eu^{3+} , Sb^{3+} , Mn^{2+} , Ag^{+} , Cu^{+} , Sn^{2+} and Tb^{3+} .
4. The luminescent regenerated cellulose fiber of any one of claims 1 to 3, wherein barium magnesium aluminate or strontium aluminate, each doped with Eu^{2+} ; yttrium oxide doped with Eu^{3+} ; calcium halophosphate or zinc silicate,

each doped with Mn^{2+} or Sb^{3+} ; strontium magnesium orthophosphate doped with Sn^{2+} ; or cerium magnesium aluminate doped with Tb^{3+} is used.

5 5. The luminescent regenerated cellulose fiber of any one of claims 1 to 4, wherein the inorganic luminophors are present in an amount of 0.01 to 5% by weight based on the cellulose content of the spinning dope prior to coagulation and shaping.

10

6. The luminescent regenerated cellulose fiber of claim 5, wherein the inorganic luminophors are present in an amount of 0.2 to 3% by weight based on the cellulose content of the spinning dope prior to coagulation and shaping.

15

7. The luminescent regenerated cellulose fiber of any one of claims 1 to 6, wherein the inorganic luminophors have an average particle size of less than 1 μm .

20 8. The luminescent regenerated cellulose fiber of claim 7, wherein the inorganic luminophors have an average particle size of 0.5 to 0.7 μm .

9. The luminescent regenerated cellulose fiber of claim
25 1, substantially as described in any one of Examples 1 to 6.

10. A process for producing luminescent regenerated

cellulose fiber, which comprises adding an activator-doped inorganic luminophor to viscose dope and spinning fiber by the viscose spinning process, or adding an activator-doped inorganic luminophor to a cellulose solution and spinning
5 fiber from the solution.

11. The process of claim 10, wherein fiber is spun by the cupro process, the lyocell process or the process involving low degree of substitution cellulose ethers.

10

12. The process of claim 10 or 11, wherein the luminophor and activator are as defined in any one of claims 1 to 8.

15

13. The process of claim 10, carried out substantially as described in any one of Examples 1 to 6.

20

14. A process for producing luminescent regenerated cellulose fiber, which comprises adding the activator-doped inorganic luminophor to the viscose dope and spinning fiber by the viscose spinning process, or adding the luminophor to a cellulose solution and spinning fiber from the solution.